



TT-537 Seal & Bond MS Rudelim

ONE-COMPONENT ADHESIVE

- ✓ Positive euro NCAP drive test after 1 hour.
- ✓ Crashtest certificate FMVSS 212 after 1h with airbag.
- ✓ Stable, high initial strength and torsional rigidity.
- ✓ Very high tensile strength, without primer, on varnish, varnish, bare metals, aluminum, galvanized,

Technical Info

- Basis: MS polymer.
- Colour: black.
- Relative density: 1.5g/m².
- Viscosity: paste.
- Shore hardness (DIN 53503): 50 Shore A after three weeks at 23 °C / 50% relative air humidity.
- Shrinkage (DIN52451): < 5%.
- Density (DIN EN 27390): non-sagging up to a 40 mm thick joint.
- Tensile strength at break: > 450%.
- Module at 100% strength: 1.0 N/mm² 23°C (DIN 53504 S2).
- Tensile strength (DIN 53504 S2): 2.3 N/mm².
- Skin formation: +/- 5 min.
- Tack free: after 24 hours 2.5 mm, after 48 hours 3.5 mm.
- Hardening speed: 6 hours at 23°C at R.V. of 50%.
- Temperature limits: from -40°C to 90 °C.
- Application temperature: lowest +5 °C – highest 40 °C.
- Chemical strength:
 - good with water, seawater, aliphatic solvents, oils, grease, thinned organic acids and lyes;
 - average: ester, ketone bodies and aromatics;
 - poor: concentrated acids, chloride solvents;

Product

Characteristics

Seal & Bond MS Rudelim is a 1-component adhesive based on MS Polymers that hardens due to air humidity. Seal & Bond MS Rudelim requires no primer and dries quickly. Seal & Bond MS Rudelim has a high initial adhesion and an excellent permanent adhesion to varnishes, bare metals, glass, PVC, aluminum. Seal & Bond MS Rudelim has a high tensile strength and shows no signs of age. Easy removal of non hardened adhesive residues. Opened cartridge can be stored for a long time.

- Storage life: 12 months, dry, cool and frostfree.
- Safety measures: please consult the safety data sheet.

Packing

TT-537 Seal & Bond MS Rudelim - cartridge
290ml

537396118

Use

- Remove at least a part of the old windscreen adhesive.
- Degrease the adhesive surface with TT-1014 Sikker Afrens FS and blow dry.
- Clean the windscreen with TT-1014 Sikker Afrens FS and TT-1004 Multifoam: spray, wipe with a cloth and wipe off with a cloth clean.
- Apply Seal & Bond MS Rudelim equally to the vehicle or on the window.
- Open the windows, place the windscreen press, correct and apply more pressure if necessary (within 2 minutes).